

Technical Data Sheet

StoCrete SFH

Standard cementitious floor hardener



Characteristics

Area of application	<ul style="list-style-type: none"> ▪ Warehouses ▪ Industrial factories ▪ Car parks and ramps ▪ Loading areas ▪ Workshops
----------------------------	---

Properties

- Hard, abrasion resistant surface
- Greater surface density which increases resistance to penetration by oil and grease
- Forms a monolithic bond with base concrete
- Contains non-metallic aggregates which are non-rusting
- Non-slip properties attainable
- Easy application using dry shake method
- Very economical flooring system
- Ready-to-use factory blend eliminating mixing error
- Available in a range of colours

Technical Data

Criteria	Standard / test specification	Value / Unit	Notes
Compressive strength	ASTM C109	> 80 N/mm ²	
Flexural strength	BS EN 1015	> 12.9 N/mm ²	
Abrasion resistance	EN 13892-4	< 0.2 mm	
Moh's hardness	EN 101	8	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

Application

Application temperature	Lowest application temperature: +8°C Highest application temperature: +45°C
--------------------------------	--

Consumption	Type of application	Approx. coverage
	Coverage rate depending on wear requirement.	4 – 7 kg/m ²

Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.

Technical Data Sheet

StoCrete SFH

Application method	Apply by power-float	
Application	<ol style="list-style-type: none"> 1) The base concrete shall be minimum Grade 30 with water / cement ratio not exceeding 0.55. 2) Base concrete slab should be placed and levelled in accordance with good concrete practice taking care to ensure the bay edges and corners are well compacted. 3) Once the base concrete slab is levelled, sprinkle StoCrete SFH along the edges and compact into the surface using a steel trowel. 4) Quantify the floor area and divide into bays. Layout sufficient materials to meet the specified coverage rate. 5) Timing for application is crucial and the 'readiness' of the base concrete must be determined. A common rule-of-thumb practice is when light foot traffic leaves an approximate 3 mm imprint. 6) StoCrete SFH is applied in two stages. Use $\frac{1}{2}$ to $\frac{2}{3}$ of the specified dosage in the first application and broadcast evenly over the bay area. Allow it to darken showing sufficient absorption of moisture from base concrete. Then power float using disc attachment. For inaccessible areas, use hand-trowel to ensure full compaction. 7) When complete, broadcast the remaining of the material at a direction perpendicular to the first application. 8) Allow second application to darken (longer than point 6) and then float it the same way as before. 9) When concrete is stiff enough so that it will not be damaged, finish the floor using a power float with blades slightly tilted. 10) Cure the treated surface with StoCretec products e.g (StoCryl ACC, StoCryl SCC) or conventional methods such as water cure or plastic sheets. <p>Note: If the concrete floor is to receive subsequent finishes such as epoxy coating etc. no curing compound should be use.</p>	
Cleaning the tools	Tools must be cleaned immediately after use with cleaning water.	
Notes, recommendations, special information, miscellaneous	Please consult the local sales office for further information and any site assistance required.	
Delivery		
Colour	Natural Grey, Blue, Green, Red	
Packaging	Name	Packing
	StoCrete SFH	25 kg
Storage		
Storage conditions	Store in cool dry conditions; avoid direct sunlight.	
Storage life	This product has a shelf life of 12 months from the manufacturing date.	
Identification		
Product group	Mortar and Floor Hardener	
Safety	Please refer to Safety Data Sheet.	

Technical Data Sheet

StoCrete SFH

Special Notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on www.sto-sea.com.

Sto SEA Pte Ltd
159 Sin Ming Road
#06-02 Amtech Building
Singapore 575625
Phone: +65 6453 3080
Fax : +65 6453 3543
info.sg@sto.com
www.sto-sea.com

Sto SEA Sdn Bhd
28, Jalan Rajawali 3
Bandar Puchong Jaya,
47170 Selangor, Malaysia
Phone: +60 3 8080 9066
Fax: +60 3 8080 9255
info.my@sto.com
www.sto-sea.com

Sto SEA Pte Ltd
3656/49-52 Green Tower, 16th Floor
Rama IV Rd, Klongton, Klongtoei,
10110 Bangkok, Thailand
Phone: +66 2 1684 921 Ext. 230
Fax: +66 2 1684 999
info.sg@sto.com
www.sto-sea.com

StoCretec GmbH
Gutenbergstr. 6
65830 Kriftel,
Germany
Phone: +49 6192 401 104
Fax: +49 6192 401 105
info.sg@sto.com
www.sto-sea.com

*Product images may differ from the actual product.