

Technical Data Sheet

StoCrete NSG

General purpose, high performance, pumpable non-shrink precision grout





Characteristics				
Area of application	 To provide heavy duty support beneath load bearing units Concrete repairs and pressure grouting 			
Properties	Ease of application			
	 Positive expansion to ensure effective contact and support 			
	 Minimal downtime 			
	Elimination of site batching errorsHigh early strength and low permeability			
	 Chloride-free permitting use in contact with reinforced steel 			
	 Good flow characteristics to allow ease of application 			
	 Good pumping properties 			
Application method	Apply using grout pump or manual pouring			

Technical Data

Criteria	Standard / test specification	Value / Unit	Notes
Compressive strength (Flowable)	ASTM C942		
@ 1 day		30 N/mm ²	
@ 7 days		60 N/mm ²	
@ 28 days		70 N/mm ²	
Compressive strength (Trowellable)	ASTM C109		
@ 1 day		48 N/mm ²	
@ 7 days		70 N/mm ²	
@ 28 days		80 N/mm ²	
Expansive characteristics	ASTM C940		
@ 3 days		< 0.2 %	
@ 28 days		< 0.2 %	
Setting time	ASTM C953		
Initial set		2.0 hours	
Final set		2.5 hours	
Final bleeding @ 3 hours	ASTM C940	< 0.2 %	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.



Technical Data Sheet

StoCrete NSG

Substrate

Preparation

- 1. All concrete surfaces to be grouted must be sound, clean and free from oil, grease, laitance or any other loose adhering particles.
- 2. Formworks shall be sufficiently tight-fitting and sealed against leakages.
- 3. On the placement side, the forms should be constructed above the bottom of the plate to form a head-box. The head-box should be positioned at a minimum of 50 mm from the plate and slope away at a 45° angle to assist grout placement as well as prevent air entrapment.
- 4. A minimum grout head (adjacent height of the slope form) of 100 mm must be maintained. In general, this can be established as 1/5 of the travel distance for the grout.
- 5. On the opposite side, the form should be minimum 50 mm away from the plate and extend at least 25 mm above the bottom of the plate.
- 6. Non-absorbent formwork is preferred; otherwise, it should be properly oiled to prevent grout adhesion.
- 7. Thoroughly wet all surfaces prior placement and remove any excess water just before introducing the grout. Bolt holes to be grouted should be cleaned of all debris, dirt and water by oil-free compressed air or vacuum.

Application

Material Preparation

- 1. Pour 4.2 4.4 litres of clean potable water into a mixing container.
- 2. With the mixer running, slowly add in the total content of the grout.
- 3. Mix continuously for about 3-5 minutes until a smooth and even consistency is obtained.
- Flow consistency should be checked and care should be taken to ensure the grout will not bleed.

Placing Procedure

Placing

- The mixed grout should be placed promptly before it stiffens. Higher temperature will accelerate working time.
- StoCrete NSG can be placed in thickness from 20 mm to 100 mm in a single pour. For
 thicker section, it is necessary to fill out the grout using well graded, cleaned aggregates
 in sizes range of 4 mm 10 mm. Quantity of aggregate added to the grout should not
 exceed 1 part aggregate to 1 part grout by weight.
- 3. Pour grout from one side only to avoid air entrapment.
- 4. Adequate grout head must be maintained at all time to achieve a continuous flow.
- Use a rod or strap to assist in large/difficult placement as well as to facilitate maximum surface contact.

Curing

As soon as the surface sheen disappear and the grout has begun to stiffen, water pond or cover with damp hessian, plastic sheet or other approved means such as Sto curing compound to prevent premature drying.



Technical Data Sheet

StoCrete NSG

Yield / Consumption	One 25 kg bag of StoCrete NSG will yield approximately 0.0130 - 0.0135 m ³ of fluid grout.			
	Consistency on Mixing	Water content (litres / 25 kg bag)		
	Flowable	4.2 – 4.4		
	Trowellable	3.5 – 3.8		
Application Temperature	Minimum application temperature + 8°C			
	Maximum application temperature + 45°C			
Cleaning Tools	Tools can be cleaned immediately after use with water.			
Delivery				
Packing	StoCrete NSG is available in 25 kg bag.			
Storage				
Storage Life & Condition	This product has a shelf life of 12 months from the manufacturing date. Product should always be stored in an unopened bag, dry place, protected from rain, direct sunlight and raised off the floor.			
Special notes				
Health & Safety	Please refer to Safety Data Sheet			
Technical Support	Please consult the local sales office for further information and any site assistance required.			
	The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.			
	Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.			
	When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on www.sto-sea.com .			

Sto SEA Pte Ltd

159 Sin Ming Road #06-02 Amtech Building Singapore 575625 Phone: +65 6453 3080 Fax: +65 6453 3543 info.sg@sto.com

www.sto-sea.com

Sto SEA Sdn Bhd

28, Jalan Rajawali 3 Bandar Puchong Jaya, 47170 Selangor, Malaysia Phone: +60 3 8080 9066 Fax: +60 3 8080 9255 info.my@sto.com www.sto-sea.com

Sto SEA Pte Ltd

3656/49-52 Green Tower, 16th Floor Rama IV Rd, Klongton, Klongtoei, 10110 Bangkok, Thailand Phone: +66 2 1684 921 Ext. 230 Fax: +66 2 1684 999 info.sg@sto.com www.sto-sea.com

StoCretec GmbH

Gutenbergstr. 6 65830 Kriftel, Germany

Phone: +49 6192 401 104 Fax: +49 6192 401 105 info.sg@sto.com www.sto-sea.com

^{*}Product images may differ from the actual product.