


# Technical Data Sheet

## StoSilent Top Finish

Organic, porous finishing coat for StoSilent acoustic systems



### Characteristics

<b>Area of application</b>	<ul style="list-style-type: none"> <li>Interior</li> <li>As a finishing coat for the StoSilent Direct, StoSilent Distance S/C/F</li> </ul>
<b>Properties</b>	<ul style="list-style-type: none"> <li>Porous</li> <li>Ultra-fine grain size</li> </ul>
<b>Appearance</b>	<ul style="list-style-type: none"> <li>Matt</li> <li>Smooth surface</li> </ul>
<b>Information/notes</b>	<ul style="list-style-type: none"> <li>Porosity is produced by means of a special application technique</li> </ul>

### Technical Data

Criteria	Standard / test specification	Value / Unit	Notes
Density	EN ISO 2811	1.4 - 1.6 g/cm <sup>3</sup>	
Water vapour diffusion- equivalent air layer thickness $\mu$	EN ISO 7783		V1 high
Reaction to fire	EN 13501-1	A2-s1, d0	
PH value		8.0 - 9.0	
Light reflectance value		77	
Degree of whiteness		69 %	

The characteristic values stated are average values or approximate values. Due to the natural raw materials in our products, the stated values can vary slightly in the same delivery batch; this does not affect the suitability of the product for its intended use.

### Substrate

**Requirements** The substrate must be even and free of ridges. The substrate must be firm, dry, clean, load-bearing, and free from sinter layers, efflorescence and release agents. Damp or not fully cured substrates can lead to defects in subsequent coats, such as changes in colour shade, blisters, or cracks. Do not use the product on damp or soiled substrates.

**Preparation** Check the surface to be coated.  
Protruding material: remove ridges in the surface and in the edge zone with caution.

### Application

**Application temperature** Lowest substrate and application temperature: +12°C at max. 70 % relative humidity

**Material preparation** The product is ready-to-use. Dilute the product with max. 2 % water.  
When using StoSilent Top Finish tinted, less water needs to be added to achieve application consistency than for untinted material.  
Stir the material well before application.

## Technical Data Sheet

# StoSilent Top Finish

<b>Consumption</b>	Type of application	Approx. consumption
	As finish	3.00 kg/m <sup>2</sup>
<p>Material consumption depends on the application, substrate, and consistency, among other factors. The stated consumption values are only to be used as a guide. If required, determine precise consumption values on the basis of the specific project.</p>		
<b>Coating build up</b>	<p>Acoustic carrier board: StoSilent Board 100, StoSilent Board 105, StoSilent Board 205, StoSilent Board MW 100</p> <p>Intermediate coat: StoSilent Top Basic</p> <p>Finish: StoSilent Top Finish</p>	
<b>Application</b>	<p>Manually</p> <p><u>Step 1:</u> Apply StoSilent Top Basic to the acoustic carrier boards with the Sto-Swiss Smoothing Trowel Notched (4 x 4) starting at the edge and transversely to the main light incidence direction. It is vital that enough material is applied during this work step. At this stage, appearance is of secondary importance</p> <p><u>Step 2:</u> Comb off the fresh layer with the Sto-Swiss Smoothing Trowel Notched (4 x 4) in a criss-cross pattern. The first notching runs transversely to the main light incidence direction, the second notching runs parallel.</p> <p><u>Notching 1:</u> Press the finishing trowel strongly and uniformly at an angle of approx. 30° - ideally until scraping is heard. Do not comb off the material in the edge zone (approx. 3 cm in width), in order to later smooth the visually flawless coating.</p> <p><u>Notching 2:</u> Comb off the layer with the Sto-Swiss Smoothing Trowel Notched (4 x 4) parallel to the main light incidence direction. Applying uniform pressure, smooth the coating using a Sto rust-free finishing spatula, holding it at an angle of approx. 10°. When smoothing, trowel off as little material as possible.</p> <p>Smooth first the edge zones and then the entire surface. To conclude deburr the entire surface. After the surface becomes matt, smooth the coating (depending on the ambient room temperature and humidity after approx. 15 - 45 minutes). First smooth the edge zone with the special plastic Sto-Finishing Trowel Profi (1 mm). Then smooth the entire surface starting from the edge zone with the Sto-Special Smoothing Trowel. Observe the current application guidelines of the respective acoustic system. In glancing light the ceilings are not free from visible unevenness.</p> <p>Renovation and cleaning: See the StoSilent Planning Manual or obtain information from a Sto technical consultant.</p>	

## Technical Data Sheet

### StoSilent Top Finish

**Drying, curing, ready for next coat** High humidity, low temperature and reduced air exchange prolong the drying time. fully dry: after approx. 36 hours

**Cleaning the tools** Clean tools with water immediately after use.

**Notes, recommendations, special information, miscellaneous** Observe the general Sto application guidelines for StoSilent acoustic systems..  
Only install and/or coat the product after training.  
Recommendation: installation on walls outside areas subject to a risk of impact, above a height of 2 m.

#### Delivery

**Colour shade** White (approx. RAL 9016), limited tintability in accordance with the StoColor System

Colour accuracy:  
Colour shade differences between the batches are possible due to the use of natural raw materials. Only apply products from the same batch to a surface.

Due to the chemical and physical setting processes at different project conditions, it is not possible to give any warranty for uniform colour accuracy and freedom from stains especially with regard to:

- uneven absorption of the substrate
- different substrate moisture levels
- partially very different alkalinity/substances in the substrate.

Note:  
Tinted product versions contain small amounts of solvent due to the pigment pastes.

Packaging	Article number	Name	Packing
	02579-003	StoSilent Top Finish	20 kg/pail

#### Storage

**Storage conditions** Store in cool dry conditions; avoid direct sunlight.

**Storage life** The quality of the product in its original container is guaranteed until the maximum storage life has expired. The storage life information is included in the batch number on the container.

Explanation of batch no.:  
Digit 1 = last digit of the year  
Digits 2 + 3 = calendar week  
Example: 6450013223 - storage life ends week 45 in 2026

#### Identification

**Product group** Acoustic coating

**Safety** Please refer to Safety Data Sheet.

## Technical Data Sheet

---

# StoSilent Top Finish

### Special Notes

The information in this Technical Data Sheet serves to ensure the product's intended use, or its suitability for use, and is based on our findings and experience. Users are nevertheless responsible for establishing the product's suitability and use.

Applications not specifically mentioned in this Technical Data Sheet are permissible only after prior consultation. Where no approval is given, such applications are at the user's own risk. This applies in particular when the product is used in combination with other products.

When a new Technical Data Sheet is published, all previous Technical Data Sheets are no longer valid. The latest version is available on [www.sto-sea.com](http://www.sto-sea.com).

**Sto SEA Pte Ltd**  
159 Sin Ming Road  
#06-02 Amtech Building  
Singapore 575625  
Phone: +65 6453 3080  
Fax : +65 6453 3543  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**Sto SEA Sdn Bhd**  
28, Jalan Rajawali 3  
Bandar Puchong Jaya,  
47170 Selangor, Malaysia  
Phone: +60 3 8080 9066  
Fax: +60 3 8080 9255  
[info.my@sto.com](mailto:info.my@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**Sto SEA Pte Ltd**  
3656/49-52 Green Tower, 16<sup>th</sup> Floor  
Rama IV Rd, Klongton, Klongtoei,  
10110 Bangkok, Thailand  
Phone: +66 2 1684 921 Ext. 230  
Fax: +66 2 1684 999  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

**Sto SE & Co. KGaA**  
Ehrenbachstrasse 1  
79780 Stühlingen,  
Germany  
Phone: +49 7744 57-0  
Fax: +49 7744 57-2178  
[info.sg@sto.com](mailto:info.sg@sto.com)  
[www.sto-sea.com](http://www.sto-sea.com)

\*Product images may differ from the actual product.